




Technical Data Sheet.

Permasolid® 1K UV-TEC Primer Surfacer 9003



UV drying, 1K Primer Surfacer for ultra-quick minor damage repairs

The Permasolid UV-TEC Primer Surfacer 9003 is a 1K, semi-transparent grey primer surfacer for bodyshops who want to improve productivity. It dries in one minute using most commercially-available LED UV lamps, and can be sanded as soon as it is cured. It can be applied directly to a variety of substrates in 2 coats, without the need for a hardener or a thinner. Also suitable for plastic substrates, which must be pre-treated with a plastic adhesion promoter. The UV primer surfacer is suitable for recoating with all Spies Hecker base coats and topcoats.

- Lightning-fast curing process
- Highly productive, short flash-off time
- 1K technology, ready-for-use, no need for a hardener or a thinner
- Reduced waste due to 1K technology
- Superior adhesion for a better corrosion resistance
- Excellent spraying and sanding properties
- CMR-chemical-free formulation
- Suitable for ultra-fast spot repairs
- Also available as aerosol

For professional use only!

Spies Hecker simply closer.




An Axalta Coating Systems Brand

Permasolid® 1K UV-TEC Primer Surfacer 9003

Product preparation - application PERMASOLID UV-TEC PRIMER-SURFACER 9003



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned
Galvanised steel or aluminium sanded and cleaned
Old or original paintwork well sanded and cleaned.
OEM Primer (e-coat), sanded and cleaned.
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.
Substrates should not be sanded coarser than with P240 abrasive (orbital machine sanding) prior overcoating with UV filler.
Rigid & half rigid types of plastics primed with Priomat Elastic Adhesion Primer 3400 after preparation (cleaning/tempering/cleaning).



Ready to use



Not applicable



	Spray nozzle	Spray pressure	
Compliant	1.1 - 1.2	1.5 - 1.8 bar	inlet pressure
HVLP	1.1 - 1.2	0.7 bar	atomisation pressure

see manufacturer's instructions



2 coats
Do not apply to coverage.

intermediate flash-off 30 sec.
final flash-off 90 sec.



All listed data is related to IRT UV SmartCure 395 LED handlamp.
1-2 min at a distance of 10-15 cm to the object.
On putty/stopper spots the UV primer surfacer has to be cured for 2 min.
A sufficient through hardening and adhesion is dependent on: Dry film thickness, intensity of the light bulb (decreasing over working time), distance to the object (increasing the lamp distance decreases the UV intensity on the surface) and curing time. Permasolid 1K UV-TEC Primer Surfacer 9003 is slightly transparent in order to achieve good through curing. Do not apply to coverage.
LED UV lamp 395nm.



P500 - P600
P800 - P1000



Basecoat + Clearcoat
2K Topcoat

VOC compliant

2004/42/IIB(c)(540) 360: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 360 g/l.

Permasolid® 1K UV-TEC Primer Surfacer 9003


Products

Permasolid® 1K UV-TEC Primer Surfacer 9003

Product mix



Mixing ratios with special agents are available in the productmix table on Phoenix and in the specific TDS.



80 - 100 µm

If higher film builds are needed, intermediate drying under UV-light is necessary before re-application of further coats. An intermediate sanding in the course of this process is not required.



Clean after use with a suitable solventbased guncleaner.

Remarks

- Material has to be at room temperature (18-25°C) before use.
- Hand stir well before pouring.
- Surplus material should not be returned to the original can.
- Spray gun should be equipped with light-proof gravity cups.
- With regards to elastifying properties, the use of an Elasticator is not recommended.
- Follow strictly the operational instructions of the drying equipment manufacturer.
- Alternative LED UV lamps with 395nm wave length and comparable intensity are useable.
- If intensity is lower, curing time and distance have to be adjusted.
- On bare steel, galvanised steel and aluminium, Pretreatment Wipes can be applied upfront for improved corrosion protection and adhesion.
- The use of UV undercoats is not recommended for repairs of substrates overcoated with matt finishes.

Permasolid® 1K UV-TEC Primer Surfacer 9003

Drying by UV-A radiation - The handling of ultraviolet radiation sources requires particular care. Only with an appropriate handling of a licensed ultraviolet drying equipment potential dangers can be avoided. - Follow strictly the operating and safety instructions of the producer of the UV-A drying equipment. - The following UV protection for skin and eyes should be used: - Wearing UV protective safety goggles, gloves and clothes.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Spies Hecker product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Spies Hecker product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.